


## TECHNICAL SHEET

### LEATHER NABUK RUSTIC

	METHOD	VALUE
Thickness	1,3-1,5 mm	
Leather Types	Nabuk - Throught dyeing aniline	
Raw Material	European raw hides	
Tonnage	Chromium salt	
COLOR RUB FASTNESS: – DRY 500 cycles	UNI EN ISO 11640:2000	>= 3 Grey scale
COLOR FASTNESS TO LIGHT	UNI EN ISO 105-B02	>= 3 Blue scale
TEAR STRENGHT	UNI EN ISO 3377-1:2012	>= 20 N
FLAMMABILITY - MATCH TEST	UNI EN ISO 1021-2:2006	No Ignition
FLAMMABILITY - CYGARETTE TEST	UNI EN ISO 1021-2:2006	No Ignition

#### MANUTENZIONE (cleaning)



#### NOTE

This item complies qith the 3M test for oleo and hydro repellency. The Scotchgard treatment gives more protection and durability to leather.