




TECHNICAL SHEET

LEATHER SOFT

	METHOD	VALUE
Thickness	1,4-1,6 mm	
Leather Types	Pigmented - Corrected Grain - Through dyeing aniline	
Raw Material	European raw hides	
Tonnage	Chromium salt	
COLOR RUB FASTNESS: – DRY 1.000 cycles – WET 250 cycles – ALKALINE SOLUTION 80 cycles	UNI EN ISO 11640:2000	>= 4 Grey scale >= 4 Grey scale >= 4 Grey scale
COLOR FASTNESS TO LIGHT	UNI EN ISO 105-B02	>= 6 Blue Scale
ADHESION OF FINISH DRY	UNI EN ISO 11640:2009	>= 2 N/10mm
TEAR STRENGTH	UNI EN ISO 3377-1:2012	>= 20 N
FLEX RESISTANCE - 50.000 cycles	UNI EN ISO 5402-1:2012	No cracks
FLAMMABILITY - MATCH TEST	UNI EN ISO 1021-2:2006	No Ignition
FLAMMABILITY - CYGARETTE TEST	UNI EN ISO 1021-2:2006	No Ignition

CLEANING AND MAINTENANCE



NOTES